

BRADY B-619 MATTE WHITE POLYESTER LABEL STOCK

TDS No. B-619
Effective Date: 09/26/2019

Description:

GENERAL

Print Technology: Dot Matrix
Material Type: White Polyester
Finish: Matte
Adhesive: Permanent Acrylic

APPLICATIONS

General purpose high performance labels, barcode labels, and topside of printed circuit board and IC identification.

RECOMMENDED RIBBONS

Brady Series R5000

REGULATORY

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

- In Canada: www.bradycanada.ca/weee-rohs
- In Europe: www.bradyeurope.com/rohs
- In Japan: www.brady.co.jp/products/labelsuse/rohs
- All other regions: www.bradyid.com/weee-rohs

SPECIAL FEATURES

Brady B-619 has good smudge resistance, solvent resistance, and high temperature performance.

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 - Topcoat - Film - Adhesive - Total (excluding liner)	0.0006 inch (0.015 mm) 0.0020 inch (0.051 mm) 0.0010 inch (0.025 mm) 0.0036 inch (0.091 mm)
Adhesion to:	ASTM D 1000	
-Stainless Steel	20 minute dwell 24 hour dwell	46 oz/in (50 N/100 mm) 55 oz/in (60 N/100 mm)
-Textured ABS	20 minute dwell 24 hour dwell	8 oz/in (9 N/100 mm) 9 oz/in (10 N/100 mm)
-Polypropylene	20 minute dwell 24 hour dwell	26 oz/in (28 N/100 mm) 29 oz/in (32 N/100 mm)
Tack	ASTM D 2979 Polyken™ Probe Tack 0.5 second dwell	34 oz (970 g)
Tensile Strength and Elongation	ASTM D 1000 -Machine Direction -Cross Direction	42 lbs/in (736 N/100 mm), 118% 52 lbs/in (911 N/100 mm), 72%
Dielectric Strength	ASTM D 1000	7000 volts
Application Temperature	Lowest application temperature to stainless steel	50°F (10°C)

The following testing is performed with the B-619 printed with the Brady Series R5000 ribbon. All samples allowed to dwell 24 hours prior to testing.

PERFORMANCE PROPERTIES	TEST METHODS	TYPICAL RESULTS
High Service Temperature	30 days at various temperatures	Very slight topcoat darkening at 145°C; no visible effect to the print. No darkening at 120°C. Label moderately discolored but functional at 160°C.
Low Service Temperature	30 days at -94°F (-70°C)	No visible effect at -70°C
Humidity Resistance	30 days at 100°F (37°C), 95% R.H.	No visible effect
UV Light Resistance	30 days in UV Sunlighter™ 100	Very slight topcoat yellowing. No visible effect to the print.
Weatherability	ASTM G155, Cycle 1 30 days in Xenon Arc Weatherometer	Print still legible, but faded
Salt Fog Resistance	ASTM B 117 30 days in 5% salt fog solution chamber	No visible effect
Abrasion Resistance	Taber Abraser, CS-10 grinding wheels, 500 g/arm (Fed. Std. 191A, Method 5306)	Print still legible after 400 cycles

PERFORMANCE PROPERTY	SOLVENT RESISTANCE
----------------------	--------------------

Samples printed with the Brady Series R5000 ribbon. Samples laminated to aluminum panels and allowed to dwell 24 hours prior to testing. Test was conducted at room temperature except where noted. Testing consisted of 5 cycles of 10 minute immersions in the specified test fluid followed by a 30 minute recovery period. After final immersion, samples rubbed 10 times with cotton swab saturated with test fluid.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE	
	APPEARANCE OF TAPE	APPEARANCE OF R5000 PRINT
Methyl Ethyl Ketone	Slight adhesive ooze, topcoat removed when rubbed	Slight bleed, print removed when rubbed
1,1,1-Trichloroethane	Slight adhesive ooze	Slight print removed when rubbed
Isopropyl Alcohol	No visible effect	No visible effect
JP-4 Jet Fuel	Slight adhesive ooze	No visible effect
SAE 20 WT Oil	No visible effect	No visible effect
Mil 5606 Oil	No visible effect	No visible effect
Speedi Kut Cutting Oil 332	No visible effect	Slight print bleed, slight print smear when rubbed
Gasoline	No visible effect	No visible effect
Rust Veto® 377	No visible effect	No visible effect
Skydrol® 500B-4	Slight adhesive ooze, topcoat softened	Slight print bleed, slight print smear when rubbed
Super Agitene®	No visible effect	No visible effect
Alphametals BIOACT® EC- 7R™	Slight adhesive ooze	Slight print bleed, slight print smear when rubbed
Deionized Water	No visible effect	No visible effect
3% Alconox® Detergent	No visible effect	No visible effect
Genesolve® 2004	Slight adhesive ooze	Slight print bleed, slight print smear when rubbed
6% Alpha 2110 @ 70°C	No visible effect	No visible effect

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

Alconox® is a registered trademark of Alconox Co.
 BIOACT® is a registered trademark of Petroferm, Inc.
 EC-7R™ is a trademark of Petroferm Inc.
 Genesolve® is a registered trademark of Allied-Signal Inc.
 Polyken™ is a trademark of Testing Machines Inc.
 Rust Veto® is a registered trademark of the E.F. Houghton & Co.
 Skydrol® is a registered trademark of the Monsanto Company
 Sunlighter™ is a trademark of the Test Lab Apparatus Company
 Super Agitene® is a registered trademark of Graymills Corporation

ASTM: American Society for Testing and Materials (U.S.A.)

SAE: Society of Automotive Engineers (U.S.A.)

UL: Underwriters Laboratories Inc. (U.S.A.)

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units.

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY



Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289

Looking for pricing, stock, or lifecycle information?

Click below to explore more details on WIN SOURCE:

-  [View WOX-49](#) on WIN SOURCE
-  [Brady Corporation](#) Information

Optimize Your Supply Chain with WIN SOURCE Solutions

-  Global Sourcing Solution
-  Obsolete Management
-  Cost Control Management
-  Shortage Management
-  Alternative Solution
-  Excess Inventory Management