



**THE DATASHEET OF
RF03N6R8B500CT**



APPROVAL SHEET

MULTILAYER CERAMIC CAPACITORS

Microwave Series (RF)

01005 to 1111 Sizes (6.3V to 1500V)

NP0 & X8G Dielectrics

Halogen Free & RoHS Compliance



*Contents in this sheet are subject to change without prior notice.

Multilayer Ceramic Capacitors

1. INTRODUCTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

WTC RF series MLCC is used at high frequencies generally have a small temperature coefficient of capacitance, typical within the $\pm 30\text{ppm}/^\circ\text{C}$ required for NP0 (C0G) & X8G classification and have excellent conductivity internal electrode. Thus, WTC RF series MLCC will be with the feature of low ESR and high Q characteristics.

2. FEATURES

- a. High Q and low ESR performance at high frequency.
- b. Ultra low capacitance to 0.1pF.
- c. Can offer high precision tolerance to $\pm 0.05\text{pF}$.
- d. Quality improvement of telephone calls for low power loss and better performance.

3. APPLICATIONS

- a. Telecommunication products & equipments: Mobile phone, WLAN, Base station.
- b. RF module: Power amplifier, VCO.
- c. Tuners.

4. HOW TO ORDER

| <u>RF</u> | <u>15</u> | <u>N</u> | <u>100</u> | <u>J</u> | <u>500</u> | <u>C</u> | <u>I</u> |
|---------------------------|--|-------------------|--|--|---|--------------------|------------------------------|
| <u>Series</u> | <u>Size</u> | <u>Dielectric</u> | <u>Capacitance</u> | <u>Tolerance</u> | <u>Rated voltage</u> | <u>Termination</u> | <u>Packaging</u> |
| RF=Ultra High Q & Low ESR | 02=01005(0402) 03=0201 (0603) 15=0402 (1005) 18=0603 (1608) 11=0505 (1414) 21=0805 (2012) 22=1111 (2828) | N=NP0 G=X8G | Two significant digits followed by no. of zeros. And R is in place of decimal point. eg.: 0R5=0.5pF 1R0=1.0pF 100=10x10 ⁰ =10pF | A= $\pm 0.05\text{pF}$ B= $\pm 0.1\text{pF}$ C= $\pm 0.25\text{pF}$ D= $\pm 0.5\text{pF}$ F= $\pm 1\%$ G= $\pm 2\%$ J= $\pm 5\%$ | Two significant digits followed by no. of zeros. And R is in place of decimal point. 6R3=6.3 VDC 100=10 VDC 250=25 VDC 500=50 VDC 101=100 VDC 201=200 VDC 251=250 VDC 501=500 VDC 152=1500 VDC | C=Cu/Ni/Sn | T=7" reeled G= 13" reeled |

Multilayer Ceramic Capacitors

5. EXTERNAL DIMENSIONS

| Size Inch (mm) | L (mm) | W (mm) | T (mm)/Symbol | Remark | M _B (mm) |
|-------------------|---------------------|---------------------|---------------|--------|---------------------|
| 01005 (0402) | 0.40±0.02 | 0.20±0.02 | 0.20±0.02 | V # | 0.10±0.03 |
| 0201 (0603) | 0.60±0.03 | 0.30±0.03 | 0.30±0.03 | L # | 0.15±0.05 |
| 0402 (1005) | 1.00±0.05 | 0.50±0.05 | 0.50±0.05 | N # | 0.25±0.05/-0.10 |
| 0603 (1608) | 1.60±0.10 | 0.80±0.10 | 0.80±0.07 | S | 0.40±0.15 |
| | 1.60 +0.15/-0.10 | 0.80 +0.15/-0.10 | 0.50±0.10 | H | |
| 0805 (2012) | 2.00±0.15 | 1.25±0.10 | 0.60±0.10 | A | 0.50±0.20 |
| | 2.00±0.20 | 1.25±0.20 | 0.85±0.10 | T | |
| 0505 (1414) | 1.40 +0.38/-0.25 | 1.40±0.38 | 1.15±0.15 | J # | 0.25±0.25/-0.13 |
| 1111 (2828) | 2.79 +0.51/-0.25 | 2.79±0.38 | ≤ 1.78 | G # | 0.38±0.25 |



Reflow soldering only is recommended.

6. GENERAL ELECTRICAL DATA

| | | |
|---|---|------------------|
| Dielectric | NP0 | X8G |
| Size | 01005, 0201, 0402, 0505, 0603, 0805, 1111 | 0402, 0603, 0805 |
| Capacitance* | 0.1pF to 1000pF | 0.1pF~82pF |
| Capacitance tolerance | Cap<10pF: A (±0.05pF), B (±0.1pF), C (±0.25pF), D (±0.5pF) Cap≥10pF: F (±1%), G (±2%), J (±5%) | |
| Rated voltage (WVDC) | 6.3V, 10V, 25V, 50V, 100V, 200V, 250V, 500V, 1500V | 250V, 500V |
| Q* | 01005, 0201, 0402/25V~50V: Cap<30pF:Q≥400+20C; Cap≥30pF:Q≥1000 0402/100V~200V, 0603, 0805, 0505, 1111: Cap<30pF:Q≥800+20C; Cap≥30pF:Q≥1400 | |
| Insulation resistance at U _r | ≥10GΩ or R _x C≥100Ω·F whichever is smaller. | |
| Operating temperature | -55 to +125°C | -55 to +150°C |
| Capacitance change | ±30ppm/°C | |
| Termination | Ni/Sn (lead-free termination) | |

* Measured at the conditions of 25°C ambient temperature and 30~70% related humidity.

Apply 1.0±0.2V_{rms}, 1.0MHz±10% for Cap≤1000pF and 1.0±0.2V_{rms}, 1.0kHz±10% for Cap>1000pF.

7. PACKAGING DIMENSION AND QUANTITY

| Size | Thickness (mm)/Symbol | | Paper tape | |
|--------------|-----------------------|---|--------------|----------|
| | | | 7" reel | 13" reel |
| 01005 (0402) | 0.20±0.02 | V | 20,000 | - |
| 0201 (0603) | 0.30±0.03 | L | 15,000 | 70,000 |
| 0402 (1005) | 0.50±0.05 | N | 10,000 | 50,000 |
| 0603 (1608) | 0.80±0.07 | S | 4,000 | 15,000 |
| | 0.50±0.10 | H | 4,000 | - |
| 0805 (2012) | 0.60±0.10 | A | 4,000 | 15,000 |
| | 0.85±0.10 | T | 4,000 | 15,000 |
| Size | Thickness (mm)/Symbol | | Plastic tape | |
| | | | 7" reel | 13" reel |
| 0505 (1414) | 1.15±0.15 | J | 3,000 | - |
| 1111 (2828) | ≤ 1.78 | G | 2,000 | - |

Unit: pieces

Multilayer Ceramic Capacitors

8. CAPACITANCE RANGE (NP0)

| DIELECTRIC | | NP0 | | Tolerance |
|---------------------|--------------|-------|---------|-----------|
| SIZE | | 01005 | | |
| RATED VOLTAGE (VDC) | | 16 | 25 | |
| Capacitance | 0.2pF (0R2) | V | V | A, B |
| | 0.3pF (0R3) | V | V | A, B |
| | 0.4pF (0R4) | V | V | A, B |
| | 0.5pF (0R5) | V | V | A, B, C |
| | 0.6pF (0R6) | V | V | A, B, C |
| | 0.7pF (0R7) | V | V | A, B, C |
| | 0.75pF (R75) | V | V | A, B, C |
| | 0.8pF (0R8) | V | V | A, B, C |
| | 0.9pF (0R9) | V | V | A, B, C |
| | 1.0pF (1R0) | V | V | A, B, C |
| | 1.1pF (1R1) | V | V | A, B, C |
| | 1.2pF (1R2) | V | V | A, B, C |
| | 1.3pF (1R3) | V | V | A, B, C |
| | 1.5pF (1R5) | V | V | A, B, C |
| | 1.6pF (1R6) | V | V | A, B, C |
| | 1.8pF (1R8) | V | V | A, B, C |
| | 2.0pF (2R0) | V | V | A, B, C |
| | 2.2pF (2R2) | V | V | A, B, C |
| | 2.4pF (2R4) | V | V | A, B, C |
| | 2.7pF (2R7) | V | V | A, B, C |
| | 3.0pF (3R0) | V | V | A, B, C |
| | 3.3pF (3R3) | V | V | A, B, C |
| | 3.6pF (3R6) | V | V | A, B, C |
| | 3.9pF (3R9) | V | V | A, B, C |
| | 4.0pF (4R0) | V | V | A, B, C |
| | 4.3pF (4R3) | V | V | A, B, C |
| | 4.7pF (4R7) | V | V | A, B, C |
| | 5.0pF (5R0) | V | V | A, B, C |
| | 5.1pF (5R1) | V | V | B, C, D |
| | 5.6pF (5R6) | V | V | B, C, D |
| 6.0pF (6R0) | V | V | B, C, D | |
| 6.2pF (6R2) | V | V | B, C, D | |
| 6.7pF (6R7) | V | V | B, C, D | |
| 6.8pF (6R8) | V | V | B, C, D | |
| 7.0pF (7R0) | V | V | B, C, D | |
| 7.5pF (7R5) | V | V | B, C, D | |
| 8.0pF (8R0) | V | V | B, C, D | |
| 8.2pF (8R2) | V | V | B, C, D | |
| 9.0pF (9R0) | V | V | B, C, D | |
| 9.1pF (9R1) | V | V | B, C, D | |
| 10pF (100) | V | V | C, D, G | |
| 12pF (120) | V | V | F, G, J | |
| 15pF (150) | V | V | F, G, J | |
| 20pF (200) | V | V | F, G, J | |
| 22pF (220) | V | V | F, G, J | |

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

Multilayer Ceramic Capacitors

| DIELECTRIC | | NP0 | | | | | | | | Tolerance |
|---------------------|--------------|------|----|----|----|------|----|-----|------------|------------|
| SIZE | | 0201 | | | | 0402 | | | | |
| RATED VOLTAGE (VDC) | | 6.3 | 10 | 25 | 50 | 25 | 50 | 100 | 200 | |
| Capacitance | 0.1pF (0R1) | L | L | L | L | N | N | N | N | A, B |
| | 0.2pF (0R2) | L | L | L | L | N | N | N | N | A, B |
| | 0.3pF (0R3) | L | L | L | L | N | N | N | N | A, B |
| | 0.4pF (0R4) | L | L | L | L | N | N | N | N | A, B |
| | 0.5pF (0R5) | L | L | L | L | N | N | N | N | A, B, C |
| | 0.6pF (0R6) | L | L | L | L | N | N | N | N | A, B, C |
| | 0.7pF (0R7) | L | L | L | L | N | N | N | N | A, B, C |
| | 0.75pF (R75) | L | L | L | L | N | N | N | N | A, B, C |
| | 0.8pF (0R8) | L | L | L | L | N | N | N | N | A, B, C |
| | 0.9pF (0R9) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.0pF (1R0) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.1pF (1R1) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.2pF (1R2) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.3pF (1R3) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.4pF (1R4) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.5pF (1R5) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.6pF (1R6) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.7pF (1R7) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.8pF (1R8) | L | L | L | L | N | N | N | N | A, B, C |
| | 1.9pF (1R9) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.0pF (2R0) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.1pF (2R1) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.2pF (2R2) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.3pF (2R3) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.4pF (2R4) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.5pF (2R5) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.6pF (2R6) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.7pF (2R7) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.8pF (2R8) | L | L | L | L | N | N | N | N | A, B, C |
| | 2.9pF (2R9) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.0pF (3R0) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.1pF (3R1) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.2pF (3R2) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.3pF (3R3) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.4pF (3R4) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.5pF (3R5) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.6pF (3R6) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.7pF (3R7) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.8pF (3R8) | L | L | L | L | N | N | N | N | A, B, C |
| | 3.9pF (3R9) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.0pF (4R0) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.1pF (4R1) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.2pF (4R2) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.3pF (4R3) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.4pF (4R4) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.5pF (4R5) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.6pF (4R6) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.7pF (4R7) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.8pF (4R8) | L | L | L | L | N | N | N | N | A, B, C |
| | 4.9pF (4R9) | L | L | L | L | N | N | N | N | A, B, C |
| | 5.0pF (5R0) | L | L | L | L | N | N | N | N | A, B, C |
| | 5.1pF (5R1) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 5.2pF (5R2) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 5.3pF (5R3) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 5.4pF (5R4) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 5.5pF (5R5) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 5.6pF (5R6) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 5.7pF (5R7) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 5.8pF (5R8) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 5.9pF (5R9) | L | L | L | L | N | N | N | N | A, B, C, D |
| 6.0pF (6R0) | L | L | L | L | N | N | N | N | A, B, C, D | |

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

| DIELECTRIC | | NP0 | | | | | | | | Tolerance |
|---------------------|-------------|------|----|----|----|------|----|-----|---------|------------|
| SIZE | | 0201 | | | | 0402 | | | | |
| RATED VOLTAGE (VDC) | | 6.3 | 10 | 25 | 50 | 25 | 50 | 100 | 200 | |
| Capacitance | 6.1pF (6R1) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 6.2pF (6R2) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 6.3pF (6R3) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 6.4pF (6R4) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 6.5pF (6R5) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 6.6pF (6R6) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 6.7pF (6R7) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 6.8pF (6R8) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 6.9pF (6R9) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.0pF (7R0) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.1pF (7R1) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.2pF (7R2) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.3pF (7R3) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.4pF (7R4) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.5pF (7R5) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.6pF (7R6) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.7pF (7R7) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.8pF (7R8) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 7.9pF (7R9) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.0pF (8R0) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.1pF (8R1) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.2pF (8R2) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.3pF (8R3) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.4pF (8R4) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.5pF (8R5) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.6pF (8R6) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.7pF (8R7) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.8pF (8R8) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 8.9pF (8R9) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.0pF (9R0) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.1pF (9R1) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.2pF (9R2) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.3pF (9R3) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.4pF (9R4) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.5pF (9R5) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.6pF (9R6) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.7pF (9R7) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.8pF (9R8) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 9.9pF (9R9) | L | L | L | L | N | N | N | N | A, B, C, D |
| | 10pF (100) | L | L | L | L | N | N | N | N | F, G, J |
| 11pF (110) | L | L | L | L | N | N | N | N | F, G, J | |
| 12pF (120) | L | L | L | L | N | N | N | N | F, G, J | |
| 13pF (130) | L | L | L | L | N | N | N | N | F, G, J | |
| 15pF (150) | L | L | L | L | N | N | N | N | F, G, J | |
| 16pF (160) | L | L | L | L | N | N | N | N | F, G, J | |
| 18pF (180) | L | L | L | L | N | N | N | N | F, G, J | |
| 20pF (200) | L | L | L | L | N | N | N | N | F, G, J | |
| 22pF (220) | L | L | L | L | N | N | N | N | F, G, J | |
| 24pF (240) | L | L | L | L | N | N | N | N | F, G, J | |
| 27pF (270) | L | L | L | L | N | N | N | N | F, G, J | |
| 30pF (300) | L | L | L | L | N | N | N | N | F, G, J | |
| 33pF (330) | L | L | L | L | N | N | N | N | F, G, J | |
| 36pF (360) | | | | | N | N | N | N | F, G, J | |
| 39pF (390) | | | | | N | N | N | N | F, G, J | |
| 43pF (430) | | | | | N | N | N | N | F, G, J | |
| 47pF (470) | | | | | N | N | N | N | F, G, J | |
| 56pF (560) | | | | | N | N | N | N | F, G, J | |
| 68pF (680) | | | | | N | N | N | N | F, G, J | |
| 82pF (820) | | | | | N | N | N | N | F, G, J | |
| 100pF (101) | | | | | N | N | N | N | F, G, J | |

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

Multilayer Ceramic Capacitors

Approval Sheet

| DIELECTRIC | | NP0 | | | | | | | | | | Tolerance |
|---------------------|-------------|------|-----|-----|------|-----|-----|------|-----|-----|-----|-----------|
| SIZE | | 0505 | | | 0603 | | | 0805 | | | | |
| RATED VOLTAGE (VDC) | | 50 | 100 | 250 | 50 | 100 | 250 | 50 | 100 | 250 | 500 | |
| Capacitance | 0.1pF (0R1) | | | | H | H | H | | | | | A, B |
| | 0.2pF (0R2) | | | | H | H | H | A | A | A | A | A, B |
| | 0.3pF (0R3) | | | | S | S | S | T | T | T | T | A, B |
| | 0.4pF (0R4) | J | J | J | S | S | S | T | T | T | T | A, B |
| | 0.5pF (0R5) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 0.6pF (0R6) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 0.7pF (0R7) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 0.8pF (0R8) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 0.9pF (0R9) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.0pF (1R0) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.1pF (1R1) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.2pF (1R2) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.3pF (1R3) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.4pF (1R4) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.5pF (1R5) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.6pF (1R6) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.7pF (1R7) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.8pF (1R8) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 1.9pF (1R9) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.0pF (2R0) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.1pF (2R1) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.2pF (2R2) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.3pF (2R3) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.4pF (2R4) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.5pF (2R5) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.6pF (2R6) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.7pF (2R7) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.8pF (2R8) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 2.9pF (2R9) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.0pF (3R0) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.1pF (3R1) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.2pF (3R2) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.3pF (3R3) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.4pF (3R4) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.5pF (3R5) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.6pF (3R6) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.7pF (3R7) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.8pF (3R8) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 3.9pF (3R9) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.0pF (4R0) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.1pF (4R1) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.2pF (4R2) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.3pF (4R3) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.4pF (4R4) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.5pF (4R5) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.6pF (4R6) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.7pF (4R7) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.8pF (4R8) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 4.9pF (4R9) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 5.0pF (5R0) | J | J | J | S | S | S | T | T | T | T | A, B, C |
| | 5.1pF (5R1) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 5.2pF (5R2) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 5.3pF (5R3) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 5.4pF (5R4) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 5.5pF (5R5) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 5.6pF (5R6) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 5.7pF (5R7) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 5.8pF (5R8) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 5.9pF (5R9) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.0pF (6R0) | J | J | J | S | S | S | T | T | T | T | B, C, D |

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

Multilayer Ceramic Capacitors

| DIELECTRIC | | NP0 | | | | | | | | | | Tolerance |
|---------------------|-------------|------|-----|-----|------|-----|-----|------|-----|-----|---------|-----------|
| SIZE | | 0505 | | | 0603 | | | 0805 | | | | |
| RATED VOLTAGE (VDC) | | 50 | 100 | 250 | 50 | 100 | 250 | 50 | 100 | 250 | 500 | |
| Capacitance | 6.1pF (6R1) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.2pF (6R2) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.3pF (6R3) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.4pF (6R4) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.5pF (6R5) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.6pF (6R6) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.7pF (6R7) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.8pF (6R8) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 6.9pF (6R9) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.0pF (7R0) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.1pF (7R1) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.2pF (7R2) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.3pF (7R3) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.4pF (7R4) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.5pF (7R5) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.6pF (7R6) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.7pF (7R7) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.8pF (7R8) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 7.9pF (7R9) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.0pF (8R0) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.1pF (8R1) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.2pF (8R2) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.3pF (8R3) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.4pF (8R4) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.5pF (8R5) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.6pF (8R6) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.7pF (8R7) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.8pF (8R8) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 8.9pF (8R9) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.0pF (9R0) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.1pF (9R1) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.2pF (9R2) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.3pF (9R3) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.4pF (9R4) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.5pF (9R5) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.6pF (9R6) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.7pF (9R7) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.8pF (9R8) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 9.9pF (9R9) | J | J | J | S | S | S | T | T | T | T | B, C, D |
| | 10pF (100) | J | J | J | S | S | S | T | T | T | T | F, G, J |
| | 11pF (110) | J | J | J | S | S | S | T | T | T | T | F, G, J |
| | 12pF (120) | J | J | J | S | S | S | T | T | T | T | F, G, J |
| 13pF (130) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 15pF (150) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 16pF (160) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 18pF (180) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 20pF (200) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 22pF (220) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 24pF (240) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 27pF (270) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 30pF (300) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 33pF (330) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 36pF (360) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 39pF (390) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 43pF (430) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 47pF (470) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 56pF (560) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 68pF (680) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 82pF (820) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 100pF (101) | J | J | J | S | S | S | T | T | T | T | F, G, J | |
| 120pF (121) | | | | S | | | T | T | T | | F, G, J | |
| 150pF (151) | | | | S | | | T | T | T | | F, G, J | |
| 180pF (181) | | | | S | | | T | T | T | | F, G, J | |
| 220pF (221) | | | | S | | | T | T | T | | F, G, J | |

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

Multilayer Ceramic Capacitors

| DIELECTRIC | | NP0 | | | | | | Tolerance |
|---------------------|-------------|------|-----|-----|-----|-----|---------|-----------|
| SIZE | | 1111 | | | | | | |
| RATED VOLTAGE (VDC) | | 50 | 100 | 200 | 250 | 500 | 1500 | |
| Capacitance | 1.0pF (1R0) | G | G | G | G | G | G | A, B, C |
| | 1.1pF (1R1) | G | G | G | G | G | G | A, B, C |
| | 1.2pF (1R2) | G | G | G | G | G | G | A, B, C |
| | 1.3pF (1R3) | G | G | G | G | G | G | A, B, C |
| | 1.5pF (1R5) | G | G | G | G | G | G | A, B, C |
| | 1.6pF (1R6) | G | G | G | G | G | G | A, B, C |
| | 1.8pF (1R8) | G | G | G | G | G | G | A, B, C |
| | 2.0pF (2R0) | G | G | G | G | G | G | A, B, C |
| | 2.2pF (2R2) | G | G | G | G | G | G | A, B, C |
| | 2.4pF (2R4) | G | G | G | G | G | G | A, B, C |
| | 2.7pF (2R7) | G | G | G | G | G | G | A, B, C |
| | 3.0pF (3R0) | G | G | G | G | G | G | A, B, C |
| | 3.3pF (3R3) | G | G | G | G | G | G | A, B, C |
| | 3.6pF (3R6) | G | G | G | G | G | G | A, B, C |
| | 3.9pF (3R9) | G | G | G | G | G | G | A, B, C |
| | 4.0pF (4R0) | G | G | G | G | G | G | A, B, C |
| | 4.3pF (4R3) | G | G | G | G | G | G | A, B, C |
| | 5.0pF (5R0) | G | G | G | G | G | G | A, B, C |
| | 5.1pF (5R1) | G | G | G | G | G | G | B, C, D |
| | 5.6pF (5R6) | G | G | G | G | G | G | B, C, D |
| | 6.0pF (6R0) | G | G | G | G | G | G | B, C, D |
| | 6.8pF (6R8) | G | G | G | G | G | G | B, C, D |
| | 7.0pF (7R0) | G | G | G | G | G | G | B, C, D |
| | 8.0pF (8R0) | G | G | G | G | G | G | B, C, D |
| | 8.2pF (8R2) | G | G | G | G | G | G | B, C, D |
| | 10pF (100) | G | G | G | G | G | G | F, G, J |
| | 12pF (120) | G | G | G | G | G | G | F, G, J |
| | 15pF (150) | G | G | G | G | G | G | F, G, J |
| | 18pF (180) | G | G | G | G | G | G | F, G, J |
| | 22pF (220) | G | G | G | G | G | G | F, G, J |
| | 27pF (270) | G | G | G | G | G | G | F, G, J |
| | 33pF (330) | G | G | G | G | G | G | F, G, J |
| | 39pF (390) | G | G | G | G | G | G | F, G, J |
| | 47pF (470) | G | G | G | G | G | G | F, G, J |
| | 56pF (560) | G | G | G | G | G | G | F, G, J |
| | 68pF (680) | G | G | G | G | G | G | F, G, J |
| | 82pF (820) | G | G | G | G | G | G | F, G, J |
| | 100pF (101) | G | G | G | G | G | G | F, G, J |
| | 120pF (121) | G | G | G | G | G | G | F, G, J |
| | 150pF (151) | G | G | G | G | G | G | F, G, J |
| 180pF (181) | G | G | G | G | G | G | F, G, J | |
| 220pF (221) | G | G | G | G | G | G | F, G, J | |
| 270pF (271) | G | G | G | G | G | G | F, G, J | |
| 330pF (331) | G | G | G | G | G | G | F, G, J | |
| 390pF (391) | G | G | G | G | G | G | F, G, J | |
| 470pF (471) | G | G | G | G | G | G | F, G, J | |
| 560pF (561) | G | G | G | G | G | G | F, G, J | |
| 680pF (681) | G | G | G | G | G | G | F, G, J | |
| 820pF (821) | G | G | G | G | G | G | F, G, J | |
| 1000pF (102) | G | G | G | G | G | G | F, G, J | |

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

Multilayer Ceramic Capacitors

CAPACITANCE RANGE (X8G)

| DIELECTRIC | X8G | | | | Tolerance |
|-------------|---------------------|------|------|---------|-----------|
| | SIZE | 0402 | 0603 | 0805 | |
| | RATED VOLTAGE (VDC) | 200 | 250 | 500 | |
| Capacitance | 0.1pF (0R1) | N | | | A, B |
| | 0.2pF (0R2) | N | | A | A, B |
| | 0.3pF (0R3) | N | S | T | A, B |
| | 0.4pF (0R4) | N | S | T | A, B |
| | 0.5pF (0R5) | N | S | T | A, B, C |
| | 0.6pF (0R6) | N | S | T | A, B, C |
| | 0.7pF (0R7) | N | S | T | A, B, C |
| | 0.8pF (0R8) | N | S | T | A, B, C |
| | 0.9pF (0R9) | N | S | T | A, B, C |
| | 1.0pF (1R0) | N | S | T | A, B, C |
| | 1.1pF (1R1) | N | S | T | A, B, C |
| | 1.2pF (1R2) | N | S | T | A, B, C |
| | 1.3pF (1R3) | N | S | T | A, B, C |
| | 1.4pF (1R4) | N | S | T | A, B, C |
| | 1.5pF (1R5) | N | S | T | A, B, C |
| | 1.6pF (1R6) | N | S | T | A, B, C |
| | 1.7pF (1R7) | N | S | T | A, B, C |
| | 1.8pF (1R8) | N | S | T | A, B, C |
| | 1.9pF (1R9) | N | S | T | A, B, C |
| | 2.0pF (2R0) | N | S | T | A, B, C |
| | 2.1pF (2R1) | N | S | T | A, B, C |
| | 2.2pF (2R2) | N | S | T | A, B, C |
| | 2.3pF (2R3) | N | S | T | A, B, C |
| | 2.4pF (2R4) | N | S | T | A, B, C |
| | 2.5pF (2R5) | N | S | T | A, B, C |
| | 2.6pF (2R6) | N | S | T | A, B, C |
| | 2.7pF (2R7) | N | S | T | A, B, C |
| | 2.8pF (2R8) | N | S | T | A, B, C |
| | 2.9pF (2R9) | N | S | T | A, B, C |
| | 3.0pF (3R0) | N | S | T | A, B, C |
| | 3.1pF (3R1) | N | S | T | A, B, C |
| | 3.2pF (3R2) | N | S | T | A, B, C |
| | 3.3pF (3R3) | N | S | T | A, B, C |
| | 3.4pF (3R4) | N | S | T | A, B, C |
| | 3.5pF (3R5) | N | S | T | A, B, C |
| | 3.6pF (3R6) | N | S | T | A, B, C |
| | 3.7pF (3R7) | N | S | T | A, B, C |
| | 3.8pF (3R8) | N | S | T | A, B, C |
| | 3.9pF (3R9) | N | S | T | A, B, C |
| | 4.0pF (4R0) | N | S | T | A, B, C |
| 4.1pF (4R1) | N | S | T | A, B, C | |
| 4.2pF (4R2) | N | S | T | A, B, C | |
| 4.3pF (4R3) | N | S | T | A, B, C | |
| 4.4pF (4R4) | N | S | T | A, B, C | |
| 4.5pF (4R5) | N | S | T | A, B, C | |
| 4.6pF (4R6) | N | S | T | A, B, C | |
| 4.7pF (4R7) | N | S | T | A, B, C | |
| 4.8pF (4R8) | N | S | T | A, B, C | |
| 4.9pF (4R9) | N | S | T | A, B, C | |
| 5.0pF (5R0) | N | S | T | A, B, C | |
| 5.1pF (5R1) | N | S | T | B, C, D | |
| 5.2pF (5R2) | N | S | T | B, C, D | |
| 5.3pF (5R3) | N | S | T | B, C, D | |
| 5.4pF (5R4) | N | S | T | B, C, D | |
| 5.5pF (5R5) | N | S | T | B, C, D | |
| 5.6pF (5R6) | N | S | T | B, C, D | |
| 5.7pF (5R7) | N | S | T | B, C, D | |
| 5.8pF (5R8) | N | S | T | B, C, D | |
| 5.9pF (5R9) | N | S | T | B, C, D | |


| DIELECTRIC | X8G | | | | Tolerance |
|-------------|---------------------|------|------|---------|-----------|
| | SIZE | 0402 | 0603 | 0805 | |
| | RATED VOLTAGE (VDC) | 200 | 250 | 500 | |
| Capacitance | 6.0pF (6R0) | N | S | T | B, C, D |
| | 6.1pF (6R1) | N | S | T | B, C, D |
| | 6.2pF (6R2) | N | S | T | B, C, D |
| | 6.3pF (6R3) | N | S | T | B, C, D |
| | 6.4pF (6R4) | N | S | T | B, C, D |
| | 6.5pF (6R5) | N | S | T | B, C, D |
| | 6.6pF (6R6) | N | S | T | B, C, D |
| | 6.7pF (6R7) | N | S | T | B, C, D |
| | 6.8pF (6R8) | N | S | T | B, C, D |
| | 6.9pF (6R9) | N | S | T | B, C, D |
| | 7.0pF (7R0) | N | S | T | B, C, D |
| | 7.1pF (7R1) | N | S | T | B, C, D |
| | 7.2pF (7R2) | N | S | T | B, C, D |
| | 7.3pF (7R3) | N | S | T | B, C, D |
| | 7.4pF (7R4) | N | S | T | B, C, D |
| | 7.5pF (7R5) | N | S | T | B, C, D |
| | 7.6pF (7R6) | N | S | T | B, C, D |
| | 7.7pF (7R7) | N | S | T | B, C, D |
| | 7.8pF (7R8) | N | S | T | B, C, D |
| | 7.9pF (7R9) | N | S | T | B, C, D |
| | 8.0pF (8R0) | N | S | T | B, C, D |
| | 8.1pF (8R1) | N | S | T | B, C, D |
| | 8.2pF (8R2) | N | S | T | B, C, D |
| | 8.3pF (8R3) | N | S | T | B, C, D |
| | 8.4pF (8R4) | N | S | T | B, C, D |
| | 8.5pF (8R5) | N | S | T | B, C, D |
| | 8.6pF (8R6) | N | S | T | B, C, D |
| | 8.7pF (8R7) | N | S | T | B, C, D |
| | 8.8pF (8R8) | N | S | T | B, C, D |
| | 8.9pF (8R9) | N | S | T | B, C, D |
| | 9.0pF (9R0) | N | S | T | B, C, D |
| | 9.1pF (9R1) | N | S | T | B, C, D |
| | 9.2pF (9R2) | N | S | T | B, C, D |
| | 9.3pF (9R3) | N | S | T | B, C, D |
| | 9.4pF (9R4) | N | S | T | B, C, D |
| | 9.5pF (9R5) | N | S | T | B, C, D |
| | 9.6pF (9R6) | N | S | T | B, C, D |
| | 9.7pF (9R7) | N | S | T | B, C, D |
| | 9.8pF (9R8) | N | S | T | B, C, D |
| | 9.9pF (9R9) | N | S | T | B, C, D |
| 10pF (100) | N | S | T | F, G, J | |
| 11pF (110) | N | S | T | F, G, J | |
| 12pF (120) | N | S | T | F, G, J | |
| 13pF (130) | N | S | T | F, G, J | |
| 15pF (150) | N | S | T | F, G, J | |
| 16pF (160) | N | S | T | F, G, J | |
| 18pF (180) | N | S | T | F, G, J | |
| 20pF (200) | N | S | T | F, G, J | |
| 22pF (220) | N | S | T | F, G, J | |
| 24pF (240) | N | S | T | F, G, J | |
| 27pF (270) | N | S | T | F, G, J | |
| 30pF (300) | N | S | T | F, G, J | |
| 33pF (330) | N | S | T | F, G, J | |
| 36pF (360) | | S | T | F, G, J | |
| 39pF (390) | | S | T | F, G, J | |
| 43pF (430) | | S | T | F, G, J | |
| 47pF (470) | | | T | F, G, J | |
| 56pF (560) | | | T | F, G, J | |
| 68pF (680) | | | T | F, G, J | |
| 82pF (820) | | | T | F, G, J | |

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.






Multilayer Ceramic Capacitors

9. ELECTRICAL CHARACTERISTICS

Please refer ECD on website (by items) for detail ELECTRICAL CHARACTERISTICS:
<http://www.passivecomponent.com/product-search/mlcc/>



Multilayer Ceramic Capacitors



Multilayer Ceramic Capacitors



Fig. 8 ESR vs. Frequency (0603 size)



Fig. 9 ESR vs. Frequency (0805 size)



Fig. 10 Q vs. Frequency (0603 size)



Fig. 11 Q vs. Frequency (0805 size)









Fig.12 Impedance vs. Frequency. (0603 size)



Fig.13 Impedance vs. Frequency (0805 size)

Multilayer Ceramic Capacitors



Multilayer Ceramic Capacitors

10. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

| No. | Item | Test Conditions | Requirements |
|-----|----------------------------------|---|---|
| 1. | Visual and Mechanical | | * No remarkable defect. * Dimensions to conform to individual specification sheet. |
| 2. | Capacitance | 1.0±0.2Vrms, 1MHz±10% | * Shall not exceed the limits given in the detailed spec. |
| 3. | Q/ D.F. (Dissipation Factor) | Test temp.: Room Temperature. | * 01005, 0201, 0402/25V~50V: Cap<30pF,Q≥400+20C;Cap≥30pF, Q≥1000 * 0402/100V~200V, 0603, 0805, 0505, 1111: Cap<30pF:Q≥800+20C;Cap≥30pF:Q≥1400 |
| 4. | Dielectric Strength | *To apply voltage: ≤100V : 250% of rated voltage.(RF02: 300% of rated voltage). 200V ~ 300V : 200% of rated voltage. 500V ~ 999V : 150% of rated voltage. 1000V ~ 3000V : 120% of rated voltage. 4000V : 110% of rated voltage. *Duration: 1 to 5 sec. *Charge & discharge current less than 50mA. | * No evidence of damage or flash over during test. |
| 5. | Insulation Resistance | * Test temp.: Room Temperature. ≤100V : To apply rated voltage for max. 120 sec. ≥200V :To apply rated voltage (500V max.) for 60 sec. | * ≥10GΩ or RxC≥100Ω-F whichever is smaller |
| 6. | Temperature Coefficient | * With no electrical load. * Operating temperature: NP0: -55~125°C at 25°C X8G: -55~150°C at 25°C | * Capacitance change: within ±30ppm/°C; |
| 7. | Adhesive Strength of Termination | Pressurizing force : 01005: 1N 0201: 2N 0402 to 0603: 5N >0603: 10N Test time: 10±1 sec. | * No remarkable damage or removal of the terminations. |
| 8. | Vibration Resistance | * Vibration frequency: 10~55 Hz/min. * Total amplitude: 1.5mm * Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.) * Cap./DF(Q) Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. | * No remarkable damage. * Cap change and Q/D.F.: To meet initial spec. |
| 9. | Solderability | * Solder temperature: 235±5°C * Dipping time: 2±0.5 sec. | * 95% min. coverage of all metalized area. |
| 10. | Bending Test | * The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5±1 sec. * Measurement to be made after keeping at room temp. for 24±2 hrs. | * No remarkable damage. * Cap change: within ±5.0% or ±0.5pF whichever is larger. (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.) |
| 11. | Resistance to Soldering Heat | * Solder temperature: 260±5°C * Dipping time: 10±1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. | * No remarkable damage. * Cap change: within ±2.5% or ±0.25pF whichever is larger. * Q/D.F., I.R. and dielectric strength: To meet initial requirements. * 25% max. leaching on each edge. |

* "Room condition" Temperature: 15 to 35°C, Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.

Multilayer Ceramic Capacitors

| No. | Item | Test Condition | Requirements | | | | | | | | | | | | | |
|--|---|---|--|---|-------------------------------------|---|---|------------------------------------|--|-------------------------------------|---|-------------------------------------|----------------------------|--------------------------------------|---|------------|
| 12. | Temperature Cycle | * Conduct the five cycles according to the temperatures and time. | * No remarkable damage. * Cap change : within $\pm 2.5\%$ or $\pm 0.25\text{pF}$ whichever is larger. * Q/D.F., I.R. and dielectric strength: To meet initial requirements. | | | | | | | | | | | | | |
| | | <table border="1"> <thead> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30\pm3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30\pm3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table> | Step | Temp. (°C) | Time (min.) | 1 | Min. operating temp. +0/-3 | 30 \pm 3 | 2 | Room temp. | 2~3 | 3 | Max. operating temp. +3/-0 | 30 \pm 3 | 4 | Room temp. |
| Step | Temp. (°C) | Time (min.) | | | | | | | | | | | | | | |
| 1 | Min. operating temp. +0/-3 | 30 \pm 3 | | | | | | | | | | | | | | |
| 2 | Room temp. | 2~3 | | | | | | | | | | | | | | |
| 3 | Max. operating temp. +3/-0 | 30 \pm 3 | | | | | | | | | | | | | | |
| 4 | Room temp. | 2~3 | | | | | | | | | | | | | | |
| | | * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24 \pm 2 hrs at room temp. | | | | | | | | | | | | | | |
| 13. | Humidity (Damp Heat) Steady State | * Test temp.: 40 \pm 2°C * Humidity: 90~95% RH * Test time: 500+24/-0hrs. * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24 \pm 2 hrs at room temp. | * No remarkable damage. * Cap change: within $\pm 5.0\%$ or $\pm 0.5\text{pF}$ whichever is larger. * Q/D.F. value: Cap \geq 30pF, Q \geq 350; 10pF \leq Cap<30pF, Q \geq 275+2.5C Cap<10pF; Q \geq 200+10C * I.R.: $\geq 1\text{G}\Omega$. | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | |
| 14. | Humidity (Damp Heat) Load | * Test temp.: 40 \pm 2°C * Humidity: 90~95%RH * Test time: 500+24/-0 hrs. * To apply voltage : rated voltage (MAX. 500V) * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24 \pm 2 hrs at room temp. | * No remarkable damage. * Cap change: within $\pm 7.5\%$ or $\pm 0.75\text{pF}$ whichever is larger. * Q/D.F. value: Cap \geq 30pF, Q \geq 200; Cap<30pF, Q \geq 100+10/3C * I.R.: $\geq 500\text{M}\Omega$. | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | |
| 15. | High Temperature Load (Endurance) | * Test temp.: NPO: 125 \pm 3°C X8G: 150 \pm 3°C To apply voltage: (1) 10V \leq Ur<500V: 200% of rated voltage. (2) $\leq 6.3\text{V}$ or 500V: 150% of rated voltage. (3) Ur $\geq 630\text{V}$: 120% of rated voltage. * Test time: 1000+24/-0 hrs. * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24 \pm 2 hrs at room temp | * No remarkable damage. * Cap change: within $\pm 3.0\%$ or $\pm 0.3\text{pF}$ whichever is larger. * Q/D.F. value: Cap \geq 30pF, Q \geq 350 10pF \leq Cap<30pF, Q \geq 275+2.5C Cap<10pF, Q \geq 200+10C * I.R.: $\geq 1\text{G}\Omega$. | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | |
| 16. | ESR | The ESR should be measured at room temperature and tested at frequency 1 \pm 0.1 GHz. | <table border="1"> <thead> <tr> <th>01005</th> <th>0505</th> </tr> </thead> <tbody> <tr> <td>0.2pF\leqCap\leq1pF:< 700mΩ/pF</td> <td>0.4pF\leqCap<1.0pF: < 1500mΩ</td> </tr> <tr> <td>1pF<Cap\leq2pF:< 600mΩ</td> <td>1.0pF\leqCap<10pF: < 250mΩ</td> </tr> <tr> <td>2pF<Cap\leq5pF:< 500mΩ</td> <td>10pF\leqCap\leq100pF: < 200mΩ</td> </tr> <tr> <td>5pF<Cap\leq10pF:< 300mΩ</td> <td></td> </tr> <tr> <td>10pF<Cap\leq22pF:< 350mΩ</td> <td></td> </tr> </tbody> </table> | 01005 | 0505 | 0.2pF \leq Cap \leq 1pF:< 700m Ω /pF | 0.4pF \leq Cap<1.0pF: < 1500m Ω | 1pF<Cap \leq 2pF:< 600m Ω | 1.0pF \leq Cap<10pF: < 250m Ω | 2pF<Cap \leq 5pF:< 500m Ω | 10pF \leq Cap \leq 100pF: < 200m Ω | 5pF<Cap \leq 10pF:< 300m Ω | | 10pF<Cap \leq 22pF:< 350m Ω | | |
| | | | 01005 | 0505 | | | | | | | | | | | | |
| | | | 0.2pF \leq Cap \leq 1pF:< 700m Ω /pF | 0.4pF \leq Cap<1.0pF: < 1500m Ω | | | | | | | | | | | | |
| | | | 1pF<Cap \leq 2pF:< 600m Ω | 1.0pF \leq Cap<10pF: < 250m Ω | | | | | | | | | | | | |
| | | | 2pF<Cap \leq 5pF:< 500m Ω | 10pF \leq Cap \leq 100pF: < 200m Ω | | | | | | | | | | | | |
| | | | 5pF<Cap \leq 10pF:< 300m Ω | | | | | | | | | | | | | |
| | | | 10pF<Cap \leq 22pF:< 350m Ω | | | | | | | | | | | | | |
| | | | <table border="1"> <thead> <tr> <th>0201</th> <th>0402</th> </tr> </thead> <tbody> <tr> <td>0.1pF\leqCap\leq1pF:< 350mΩ/pF</td> <td>0.1pF\leqCap\leq1pF:< 350mΩ/pF</td> </tr> <tr> <td>1pF<Cap\leq5pF:< 300mΩ</td> <td>1pF<Cap\leq5pF:< 300mΩ</td> </tr> <tr> <td>5pF<Cap\leq22pF:< 250mΩ</td> <td>5pF<Cap\leq100pF:< 250mΩ</td> </tr> </tbody> </table> | 0201 | 0402 | 0.1pF \leq Cap \leq 1pF:< 350m Ω /pF | 0.1pF \leq Cap \leq 1pF:< 350m Ω /pF | 1pF<Cap \leq 5pF:< 300m Ω | 1pF<Cap \leq 5pF:< 300m Ω | 5pF<Cap \leq 22pF:< 250m Ω | 5pF<Cap \leq 100pF:< 250m Ω | | | | | |
| | | | 0201 | 0402 | | | | | | | | | | | | |
| | | | 0.1pF \leq Cap \leq 1pF:< 350m Ω /pF | 0.1pF \leq Cap \leq 1pF:< 350m Ω /pF | | | | | | | | | | | | |
| 1pF<Cap \leq 5pF:< 300m Ω | 1pF<Cap \leq 5pF:< 300m Ω | | | | | | | | | | | | | | | |
| 5pF<Cap \leq 22pF:< 250m Ω | 5pF<Cap \leq 100pF:< 250m Ω | | | | | | | | | | | | | | | |
| <table border="1"> <thead> <tr> <th>0603</th> <th>0805</th> </tr> </thead> <tbody> <tr> <td>0.1pF\leqCap\leq1pF:< 1500mΩ</td> <td>0.3pF\leqCap\leq1pF: < 1500mΩ</td> </tr> <tr> <td>1pF<Cap\leq10pF:< 250mΩ</td> <td>1pF<Cap\leq10pF: < 250mΩ</td> </tr> <tr> <td>10pF<Cap\leq220pF:< 200mΩ</td> <td>Cap>10pF: < 200mΩ</td> </tr> </tbody> </table> | 0603 | 0805 | 0.1pF \leq Cap \leq 1pF:< 1500m Ω | 0.3pF \leq Cap \leq 1pF: < 1500m Ω | 1pF<Cap \leq 10pF:< 250m Ω | 1pF<Cap \leq 10pF: < 250m Ω | 10pF<Cap \leq 220pF:< 200m Ω | Cap>10pF: < 200m Ω | | | | | | | | |
| 0603 | 0805 | | | | | | | | | | | | | | | |
| 0.1pF \leq Cap \leq 1pF:< 1500m Ω | 0.3pF \leq Cap \leq 1pF: < 1500m Ω | | | | | | | | | | | | | | | |
| 1pF<Cap \leq 10pF:< 250m Ω | 1pF<Cap \leq 10pF: < 250m Ω | | | | | | | | | | | | | | | |
| 10pF<Cap \leq 220pF:< 200m Ω | Cap>10pF: < 200m Ω | | | | | | | | | | | | | | | |
| The ESR should be measured at room temperature and tested at frequency 500 \pm 50 MHz. | | | | | | | | | | | | | | | | |
| 0201, 22pF \leq Cap \leq 33pF: < 300m Ω | | | | | | | | | | | | | | | | |
| 1111, 100pF<Cap \leq 1000pF: < 150m Ω | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | |

* "Room condition" Temperature: 15 to 35°C, Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.

Multilayer Ceramic Capacitors

APPENDIXES

■ **Tape & reel dimensions**



Fig. 21 The dimension of paper tape



Fig. 22 The dimension of plastic tape



Fig. 23 The dimension of reel

| Size | 01005 | 0201 | 0402 | 0505 | 0603 | 0805 | 1111 |
|-------------------|------------------|------------------|------------------|------------------|------------------|------------------|------------------|
| Thickness | V | L | N | J | S | T | G |
| A ₀ | 0.25 +/-0.05 | 0.40 +/-0.10 | 0.70 +/-0.20 | < 1.90 | 1.05 +/-0.30 | 1.50 +/-0.20 | < 3.05 |
| B ₀ | 0.45 +/-0.05 | 0.70 +/-0.10 | 1.20 +/-0.20 | < 1.90 | 1.80 +/-0.30 | 2.30 +/-0.20 | < 3.80 |
| T | ≤ 0.50 | ≤ 0.55 | ≤ 0.80 | 0.23 +/-0.1 | ≤ 1.20 | ≤ 1.20 | 0.23 +/-0.1 |
| K ₀ | - | - | - | < 1.50 | - | - | < 2.50 |
| W | 8.00 +/-0.30 | 8.00 +/-0.30 | 8.00 +/-0.30 | 8.00 +/-0.30 | 8.00 +/-0.30 | 8.00 +/-0.30 | 8.00 +/-0.30 |
| P ₀ | 4.00 +/-0.10 | 4.00 +/-0.10 | 4.00 +/-0.10 | 4.00 +/-0.10 | 4.00 +/-0.10 | 4.00 +/-0.10 | 4.00 +/-0.10 |
| 10xP ₀ | 40.00 +/-0.10 | 40.00 +/-0.10 | 40.00 +/-0.10 | 40.00 +/-0.20 | 40.00 +/-0.20 | 40.00 +/-0.20 | 40.00 +/-0.20 |
| P ₁ | 2.00 +/-0.05 | 2.00 +/-0.05 | 2.00 +/-0.05 | 4.00 +/-0.10 | 4.00 +/-0.10 | 4.00 +/-0.10 | 4.00 +/-0.10 |
| P ₂ | 2.00 +/-0.05 | 2.00 +/-0.05 | 2.00 +/-0.05 | 2.00 +/-0.05 | 2.00 +/-0.05 | 2.00 +/-0.05 | 2.00 +/-0.05 |
| D ₀ | 1.50 +0.1/-0 | 1.50 +0.1/-0 | 1.50 +0.1/-0 | 1.50 +0.1/-0 | 1.50 +0.1/-0 | 1.50 +0.1/-0 | 1.50 +0.1/-0 |
| D ₁ | - | - | - | 1.00 +/-0.10 | - | - | 1.00 +/-0.10 |
| E | 1.75 +/-0.10 | 1.75 +/-0.10 | 1.75 +/-0.10 | 1.75 +/-0.10 | 1.75 +/-0.10 | 1.75 +/-0.10 | 1.75 +/-0.10 |
| F | 3.50 +/-0.05 | 3.50 +/-0.05 | 3.50 +/-0.05 | 3.50 +/-0.05 | 3.50 +/-0.05 | 3.50 +/-0.05 | 3.50 +/-0.05 |

| Size | 01005, 0201, 0402, 0505, 0603, 0805, 1111 | |
|----------------|---|-----------|
| Reel size | 7" | 13" |
| C | 13.0±0.5 | 13.0±0.5 |
| W ₁ | 10.0±1.5 | 10.0±1.5 |
| A | 178.0±2.0 | 330.0±2.0 |
| N | 60.0+1.0/-0 | 50 min |

■ **Peeling force (EIA-481)**

Peel-off force should be in the range of 10 grams to 100 grams at a peel-off speed of 300±10 mm/min.



Multilayer Ceramic Capacitors

Example of customer label



- a. Customer name
- b. WTC order series and item number
- c. Customer P/O
- d. Customer P/N
- e. Description of product
- f. Quantity
- g. Bar code including quantity & WTC P/N or customer
- h. WTC P/N
- i. Shipping date
- j. Order bar code including series and item numbers
- k. Serial number of label

*Customized label is available upon request

Constructions

| No. | Name | X8G, NP0 |
|-----|------------------|-------------------------|
| ① | Ceramic material | Hi-Q dielectric ceramic |
| ② | Inner electrode | Cu |
| ③ | Termination | Inner layer |
| ④ | | Middle layer |
| ⑤ | | Outer layer |
| | | Sn (Matt) |




Fig. 24 The construction of MLCC

Storage and handling conditions

- (1) To store products at 5 to 40°C ambient temperature and 20 to 70% related humidity conditions; MSL Level 1.
- (2) The product is recommended to be used within one year after shipment. Check solderability in case of shelf life extension is needed.

Cautions:

- a. The corrosive gas reacts on the terminal electrodes of capacitors, and results in the poor solderability. Do not store the capacitors in the ambience of corrosive gas (e.g., hydrogen sulfide, sulfur dioxide, chlorine, ammonia gas etc.)
- b. In corrosive atmosphere, solderability might be degraded, and silver migration might occur to cause low reliability.
- c. Due to the dewing by rapid humidity change, or the photochemical change of the terminal electrode by direct sunlight, the solderability and electrical performance may deteriorate. Do not store capacitors under direct sunlight or dewing condition. To store products on the shelf and avoid exposure to moisture.

Multilayer Ceramic Capacitors

Recommended soldering conditions

The lead-free termination MLCCs are not only to be used on SMT against lead-free solder paste, but also suitable against lead-containing solder paste. If the optimized solder joint is requested, increasing soldering time, temperature and concentration of N₂ within oven are recommended.



Fig. 25 Recommended reflow soldering profile for SMT process with SnAgCu series solder paste.



Fig. 26 Recommended wave soldering profile for SMT process with SnAgCu series solder.



Looking for pricing, stock, or lifecycle information?

Click below to explore more details on WIN SOURCE:

- ⊖ [View RF03N6R8B500CT](#) on WIN SOURCE
- ⊖ [Walsin Technology Corporation](#) Information

Optimize Your Supply Chain with WIN SOURCE Solutions

- ✓ Global Sourcing Solution
- ✓ Obsolete Management
- ✓ Cost Control Management
- ✓ Shortage Management
- ✓ Alternative Solution
- ✓ Excess Inventory Management